

TECHNICAL DATA SHEET

Contact Treatment Grease

Contact Treatment Grease is a grease designed for use on electrical contacts to significantly increase contact performance and lifetime.

- Improves contact performance by increasing effective contact area
- Suitable for a range of plastics and rubbers (testing advised)
- Inhibited against oxidation and copper corrosion
- Excellent penetration and cooling properties; prevents arcing, thus reduces contact wear

Approvals **RoHS-2 Compliant (2011/65/EU):** Yes

Typical Properties

Colour	Beige
Density (g/ml)	1.10
Temperature Range (°C)	-30 to +125
Evaporation Weight Loss (% 7 days @ 100°C)	3.7
Copper Strip Corrosion (IP154 / ISO 2160)	≤1b
Drop Point (IP32 / ISO 2176 (°C))	250
Cone Penetration Worked (ASTM D217, 60 strokes @ 20°C)	320
Cone Penetration Un-worked (ASTM D 217 @ 20°C)	310
Consistency (NLGI)	1
Oil Bleed / Separation (IP121)	6%
Plastic Compatibility - ABS	Test
Plastic Compatibility - PC	Test
Base Oil	Poly Alkylene Glycol
Thickener	Clay
Water Content (%)	0.6
UV Trace	No

Directions for Use

Before final treatment with lubricants, contact surfaces should be clean and dry. Contact Treatment Grease can be applied by one of the following methods (although this list is not exhaustive): **Manually** by way of a syringe: **Semi-automated** using syringe dispensing. In production processes, contact lubricant should be applied to the contact components as soon as possible after manufacture or plating to protect against handling contamination and tarnishing. Contact Treatment Grease can be used on all types of electrical contacts and with most types of thermoplastics. A small area should be tested first to ensure compatibility. Contact Treatment Grease is a non-melting product that will not migrate from vertical surfaces and will provide greater environmental protection than the oil.